

PREMIUM

PLA 607

Material	PLA
Colour	NATURAL
Properties	<p>After annealing process the material mechanical properties improvement are observed. Also the printed object thermal stability rise up to 140°C.</p> <p>The heat treatment shall be performed in 80°C for 10 -25 minutes.</p> <p>Annealed objects obtains the mechanical properties similar to ABS.</p>
Diameter	1.75mm
Diameter tolerance	+/- 0.05mm
Printing temperature	190-220°C
Heatbed temperature	0-60 °C
Net weight	1kg
Gross weight	1.4kg
Spool dimensions	200x52x80mm
Packaging	Vacuum packaging, carton box